AMENDMENTS TO THE CLAIMS

- 1. (Currently Amended) An acrylic pressure-sensitive adhesive composition comprising a solution or miscible blend consisting essentially of:
 - a. <u>from 50 to 99% by weight of at least one hydrophobic C₁₋₂₂alkyl (meth)acrylate copolymer,</u>
 - b. at least one substantially water insoluble polyol <u>oligomer</u> having <u>at least two</u>

 <u>terminal hydroxyl groups and</u> a number average molecular weight of from 1000

 to 20000 and selected from the group consisting of polyester polyols, acrylic

 polyols, polycarbonate polyols and polyether polyols,
 - c. at least one <u>cross-linking agent selected from the group consisting of a transition</u>
 metal complex <u>and aluminum acetyl acetonate</u> as <u>cross-linking agent</u>.
 - d. optionally <u>at least</u> one or more tackifying resins resin,
 - e. optionally at least one or more solvents solvent, and
 - f. optionally <u>at least</u> one or more of <u>selected from the group consisting of:</u>
 plasticizers, adhesion promoters, pigments, fillers, antioxidants and UV
 stabilizers.
- 2. (Original) The acrylic pressure sensitive adhesive composition according to claim 1 wherein:
 - a. is present in an amount of about 30 to 95% by weight,
 - b. is present in an amount of about 5 to 50% by weight,
 - c. is present in an amount of about 0.05 to 2.0% by weight,
 - d. is present in an amount of up to about 50% by weight,
 - e. is present in an amount of up to about 90% by weight and
 - f. is present in an amount of about 10% by weight.

- 3. (Currently Amended) The acrylic pressure-sensitive adhesive composition according to claim 1 wherein the (meth)acrylic polymer comprises the reaction product of:
 - i) about 50 to 99 % by weight of at least one alkyl (meth)acrylate monomer having an alkyl group which contains about 1 to 22 carbon atoms;
 - ii) 0 to about 50 % by weight of at least one other monomer selected from the group consisting of alkyl (meth)acrylate monomers having an alkyl group containing about 1 to 22 carbon atoms, vinyl acetate and styrene; and
 - iii) about 0.5 to about 20% by weight of at least one polar monomer selected from the group consisting of monofunctional carboxylic acid monomers, multifunctional carboxylic acid monomers, monofunctional hydroxymonomers hydroxymonomers, multifunctional hydroxymonomers, cyanoalkyl acrylates, acrylamides, acrylonitriles, butanediol monoacrylate and vinyl pyrrolidone.
- 4. (Currently Amended) The acrylic pressure-sensitive adhesive composition according to claim 1 wherein the cross-linking agent (e) c. is selected from the group consisting of transition metal acetyl acetonates and aluminum acetyl acetonate.
- 5. (Currently Amended) The acrylic pressure-sensitive adhesive composition according to claim 1 wherein the tackifying resin d. is selected from the group consisting of:
 - i) rosin acid, polymerized rosin acid, rosin ester and mixtures thereof;
 - ii) hydrogenated rosin acid, hydrogenated rosin ester and mixtures thereof;
 - iii) polyterpene and terpene phenolic resins;
 - iv) aromatic resins consisting of a reaction product of styrene, alpha-methyl styrene, vinyl toluene and mixtures thereof; and
 - v) phenolic modified aromatic resins, benzoate resins, coumarone-indene resins, synthetic phenol resins, and mixtures thereof.

- 6. (Original) The acrylic pressure-sensitive adhesive composition according to claim 1 wherein the solvent of e. is selected from the group consisting of aliphatic esters, aliphatic hydrocarbons, halogenated aliphatic hydrocarbons, aromatic hydrocarbons, aliphatic alcohols, aliphatic ketones and mixtures thereof.
- 7. (Original) The acrylic pressure-sensitive adhesive composition according to claim 6 wherein the aliphatic hydrocarbons are heptane or hexane, the aromatic hydrocarbons are toluene or xylene, the aliphatic alcohols are methanol, ethanol or isopropanol, the aliphatic ketone is acetone and the aliphatic ester is ethyl acetate.
- 8. (Currently Amended) The acrylic pressure-sensitive adhesive composition according to claim 1 additionally containing about 0.1 to 2.0% by weight of an antioxidant or UV stabilizer.
- 9. (Original) An adhesive coated sheet material formed by coating a substrate sheet with the acrylic pressure-sensitive adhesive composition of claim 1.
- 10. (New) The acrylic pressure-sensitive adhesive composition according to claim 1 wherein the cross-linking agent c. is aluminum acetyl acetonate.